

## TECHNICAL DATA SHEET

TDS: TMW475  
530/W475/1

### GALLEY PAINT

#### DESCRIPTION:

Teamac Galley Paint has been designed to reduce condensation forming on interior surfaces. It's lightly textured surface can be overpainted with other Teamac products to provide colour.

#### RECOMMENDED USE:

Teamac Galley Paint is suitable for yachts, cruisers and narrowboats. It can be used in galleys, heads, cabins, ceilings and any area where condensation may form.

#### AVAILABILITY:

1 litre

#### FINISH:

Matt

#### COLOUR:

White

#### TYPICAL S.G. (SPECIFIC GRAVITY):

1.2 @ 20 °C

#### VOLUME SOLIDS:

41%

#### WET FILM THICKNESS W.F.T

100 to 125 microns

#### DRY FILM THICKNESS D.F.T

40 to 50 microns

#### EXPECTED SPREADING RATE:

8 to 10 sq.m / litre  
@ 40 to 50 microns D.F.T.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

#### TYPICAL VISCOSITY:

8 to 9 Poise @ 25 °C

#### FLASH POINT:

Non-flammable

#### DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 2 hours @ 20 °C

Hard dry: 4 hours @ 20 °C

Full hardness: 3 to 5 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

#### MINIMUM OVERCOATING TIME:

4 hours

#### APPLICATION SPECIAL CONDITIONS:

N/A

#### VOC CONTENT:

Max 30 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

#### APPLICATION DETAILS:

Application Do not apply below 10 °C.  
restrictions

Method: Brush or Roller

Thinner Clean Water  
(Max vol): (5%)

Nozzle size: N/A

Nozzle N/A  
pressure:

Cleaning Water  
solvent:

Recoat 4 hours  
interval:

**For further advice contact Teamac Technical Services on +44(0)1482 320194**

**The physical constants are subject to normal manufacturing tolerances.**

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

**GALLEY PAINT****530/W475/1**

---

**SURFACE PREPARATION:**

All surfaces should be clean, dry, sound and free from contaminants and grease. Scrape and brush the surface to remove any loose flaking material. Flat down glossy surfaces with abrasive paper. Treat any mould or lichen with a proprietary mould remover with a scraper or a stiff brush then treat again. Prime bare metal areas with Teamac Marine Primer Undercoat.

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 320194.

**MIXING INSTRUCTIONS:**

This paint is thick by nature and once opened will require a thorough stir before use.

**APPLICATION CONDITIONS:**

Do not apply below 10 °C. As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

**PRECEDING COAT:**

Teamac Marine Primer Undercoat on bare metal.

**SUBSEQUENT COAT:**

2 Full coats of Teamac Galley Paint.

**REMARKS:****HEALTH AND SAFETY:**

See safety data sheet - SDS 20919

**ISSUED:**

01 November 2019

**REVISION:**

0

**For further advice contact Teamac Technical Services on +44(0)1482 320194**

**The physical constants are subject to normal manufacturing tolerances.**

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

---

**TEAMAC**

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 320194. Fax: +44(0)1482 219266

Email: [info@teamac.co.uk](mailto:info@teamac.co.uk)

[www.teamac.co.uk](http://www.teamac.co.uk)